

## Technical Data Sheet Tuffbond<sup>®</sup> 312

August 2020

Page 1 of 1

### Product Description

Hernon<sup>®</sup> Tuffbond<sup>®</sup> 312 is a slow curing epoxy adhesive. Epoxy system has 2 components which need to be mixed well.

### Typical Properties (Uncured)

Property	Part A	Part B
Base	Epoxy	Amine
Appearance	White- Lt Tan	Black
Viscosity at 25°C, HBT, spindle TB, 10 rpm (cP) ASTM D2556	90,000-130,000	80,000-120,000
Specific Gravity	1.21	1.07

### Typical Properties (Cured)

Property	Value
Working Life at 22°C (20g)	3-4 hours
Durometer Hardness*, ASTM D2240	60-75 Shore A

\*Mix ratio for A:B is 1:1 by volume, hardness was measured after 168 hours RT cure.

### Typical Cured Performance

Shear Strength on G/B steel lap-shear specimens tested according to ASTM D1002.

Cure Time at 22°C	Shear Strength (psi)
16 hours	≥ 200
24 hours	≥ 300

### General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

### Storage

Tuffbond<sup>®</sup> 312 should be stored in a cool, dry location in unopened containers at a temperature between 45°F to

85°F (7°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

### Dispensing Equipment

Hernon<sup>®</sup> offers a complete line of semi and fully automated dispensing equipment. Contact Hernon<sup>®</sup> Sales for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING<sup>®</sup>, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.